

FeTi 70% Specifications	Al %	Zr	Mo	V %	Fe %	Mn %	Sn %	Si %	S %	P %	O %	C %	N %	H %	Ti %
Met 101, Standard Grade FeTi	4.00	-	-	3.00	Bal	1.00	0.05	0.05	0.02	0.02	1.50	0.15	0.40	-	68.00
	-										-	-			-
	6.00										2.00	0.30			72.00
Met 121, Low Carbon Grade FeTi	4.00	-	-	3.00	Bal	1.00	0.05	0.05	0.02	0.02	1.50	0.10	0.40	-	68.00
	-										-				-
											2.00				72.00
Met 131, Low Aluminium Grade FeTi	0.50	-	-	3.00	Bal	1.00	0.05	0.05	0.02	0.02	1.50	0.15	0.40	-	68.00
	-										-				-
	1.50										2.00				72.00
Met 151, Low Nitrogen Grade FeTi	4.00	-	-	3.00	Bal	1.00	0.05	0.05	0.02	0.02	1.50	0.15	0.20	-	68.00
	-										-				-
	6.00										2.00				72.00
Met 171, Low Vanadium Grade FeTi	4.00	-	-	0.20	Bal	1.00	0.05	0.05	0.02	0.02	1.50	0.15	0.40	-	68.00
	-			-							-	-			-
	6.00			1.00							2.00	0.30			72.00